

ACERINOX				PROPIEDADES MECÁNICAS				
	Norma Europea EN 10088		ASTM	Código	Resistencia a la Tracción	Límite Elástico al 0,2% mínimo	Alargamiento mínimo	Dureza máxima
	Nº Acero	Designación	AISI	ACX	N/mm ²	N/mm ²	%	HB
	AUSTENÍTICA	1.4301	X5CrNi18-10	304	120	540-750	230	45
---		---	304LN	130	515-700	205	30	200
1.4301		X5CrNi18-10	302	140	540-750	230	45	190
1.4307		X2CrNi18-9	304 L	150	520-670	220	45	190
1.4301		X5CrNi18-10	304	160	540-750	230	45	190
1.4301		X5CrNi18-10	304 DDQ	170	540-750	230	45	190
1.4301		X5CrNi18-10	304 DDQ	180	540-750	230	45	190
1.4301		X5CrNi18-10	304 DDS	190	540-750	230	45	190
1.4307		X2CrNi18-9	304 L	200	520-670	220	45	190
1.4404		X2CrNiMo17-12-2	316L	240	540-620	240	45	200
1.4401		X5CrNiMo17-12-2	316	250	530-680	240	45	200
1.4432		X2CrNiMo17-12-3	316 L	260	550-700	240	45	200
1.4404		X2CrNiMo17-12-2	316 L	270	530-680	240	45	200
1.4571		X6CrNiMoTi17-12-2	316 Ti	280	540-690	240	45	200
1.4436		X3CrNiMo17-13-3	316 L	290	550-700	240	45	200
1.4435		X2CrNiMo18-14-3	316 L	300	550-700	240	45	200
1.4541		X6CrNiTi18-10	321	315	520-720	220	45	200
1.4406		X2CrNiMoN17-11-02	316 LN	320	580-780	300	40	200
1.4438		X2CrNiMo18-15-4	317 L	330	550-700	240	35	200
1.4833		X12CrNi23-3	309S	340	515-700	210	40	215
1.4845	X8CrNi25-21	310 S	350	515-700	205	40	200	
FERRÍTICA	1.4000	X6Cr13	410S	420	400-600	240	19	180
	1.4016	X6Cr17	430	500	450-600	260	20	180
	1.4510	X3CrTi17	430 Ti	515	420-600	230	23	180
	1.4511	X3CrNb17	430 Nb	525	420-600	230	23	180
	1.4113	X6CrMo17-1	434	535	450-630	230	18	180
	1.4513	X2CrMoTi17-1	---	540	400-550	220	23	180
	1.4512	X2CrTi12	409L	800	380-560	210	25	170
	1.4509	X2CrTiNb18	---	845	430-630	230	18	180
MARTENSÍTICA	1.4028	X30Cr13	420	360	700max	350	15	220
	1.4034	X46Cr13	420	370	700max	350	15	230
	1.4116	X50CrMoV15	420 MoV	380	750max	350	15	230
	1.4006	X12Cr13	410	410	600max	250	20	200